

Advanced Materials**RenShape® SL 7811**

STEREOLITHOGRAPHY MATERIALS
For use on Solid State Laser SLA® Systems

ABS Like Performance
Good Durability

DESCRIPTION

RenShape® SL 7811 stereolithography material is a white, low viscosity stable liquid that produces strong white models and prototypes with good surface finish and detail, an ABS-like appearance. The product is also well suited for building RTV patterns. Parts built with SL7811 exhibit durability over time beyond 6 months.

MEASUREMENT	CONDITION	VALUE
Appearance		White liquid
Density	@ 25°C (77°F)	1.11 g/cm ³
Viscosity	@ 28°C (82°F)	240 cps
Viscosity	@ 30°C (86°F)	210 cps
Penetration depth (Dp)		5.25 mils
Critical exposure (Ec)		10.97 mJ/cm ²
Part building layer thickness*		0.10mm (0.004 in.)

* Dependent upon part geometry and build parameters.

POST-CURED MATERIAL

MEASUREMENT	TEST METHOD	VALUE 90-minute UV post-cure	VALUE 90-minute UV + 2 hours @ 80°C (176°F) thermal postcure
Hardness, Shore D	ASTM D-2240	86	86
Flexural modulus	ASTM D-790	1,500-2,200 MPa (220-320 ksi)	1,500-2,000 MPa (220-290 ksi)
Flexural strength	ASTM D-790	35-54 MPa (5,000-7,800 psi)	33-52 MPa (4,800-7,500 psi)
Tensile modulus	ASTM D-638	1,500-2,000 MPa (220-290 ksi)	1,500-2,000 MPa (220-290 ksi)
Tensile strength	ASTM D-638	34-42 MPa (4,900-6,000 psi)	34-40 MPa (4,900-5,800 psi)
Elongation at break	ASTM D-638	15-30%	15-30%
Impact strength, notched Izod	ASTM D-256	42-59 J/m (0.78-1.10 ft.-lb./in.)	43-65 J/m (0.80-1.21 ft.-lb./in.)
Heat deflection temperature	ASTM D-648 @ 66 psi @ 264 psi	47°C (117°F) --°C (--°F)	46°C (115°F) --°C (---°F)
Glass transition, Tg	DMA, E" peak	63°C (145°F)	n/a
Coefficient of thermal expansion	TMA (T<Tg) TMA (T>Tg)	92 x 10 ⁻⁶ /°C 207 x 10 ⁻⁶ /°C	n/a
Cured Density		1.15g/cm ³	n/a

CAUTION :

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 888-564-9318 or emailing your request to advanced_materials@huntsman.com.

FIRST AID !

Eyes and skin : Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation : Remove subject to fresh air.

Swallowing : Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

KEEP OUT OF REACH OF CHILDREN**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

RenShape is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2009 Huntsman Advanced Materials Americas Inc.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400