



TC-886 A/B FR RIGID 78 SHORE D POLYURETHANE CASTING SYSTEM FIRE RETARDANT

PRODUCT DESCRIPTION:

TC-886 A/B FR produces a high impact rigid 78 Shore D material that is commonly used to make computer housings, models of all kinds, artwork, and can also be used for electronic component enclosures. It provides a working time of 15 minutes.

PRODUCT HIGHLIGHTS:

- Non-mercury based catalyst system
- Odorless, clean white color
- ➤ Three to four hour demold time
- > Excellent for vacuum or pressure casting
- ➤ Low viscosity
- > UL 94 V0 Flammability Rating

PHYSICAL PROPERTIES:

Hardness, Shore D ASTM D 2240		
Density, (g/cc) ASTM D 792		
Cubic Inches per Pound	22.6	
Color/Appearance	White/Opaque	
Tensile Strength, (psi) ASTM D 638	6,100	
Tensile Modulus, (psi) ASTM D 638	2.3 x 10^5	
Elongation, (%) ASTM D 638	5	
Flexural Strength, (psi) ASTM D 790	8,600	
Flexural Modulus, (psi) ASTM D 790	2.3 x 10^5	
Shrinkage, (in./in.) linear 12" x ½" x ½"		
Izod Impact, notched (ftlb./in.) ASTM D 256	0.62	
Heat Deflection Temperature (@ 66 psi) ASTM D 648	$195^{\circ} \pm 5^{\circ} F (91^{\circ} \pm 3^{\circ} C)$	
(@ 264 psi) ASTM D 648	$180^{\circ} \pm 5^{\circ} F (82^{\circ} \pm 3^{\circ} C)$	
Note: Reported physical properties based on elevated temperature cured test specimens.		

HANDLING PROPERTIES:

Mix Ratio (by weight):	
Part A	
Part B	85 parts by weight
M' - D - d' - (l 1)	1 , 0
Part A	
Part B	
Specific Gravity:	
Part A	
Part B	

HANDLING PROPERTIES (continued):

Viscosity, (cps) @ 77°F (25°C) Brookfield:	
Part A	75
Part B	
Mixed	350
Color:	
Part A	Light amber
Part B	White
Work Time, (100 gram mass) @ 77°F (25°C)	15 minutes
Gel Time	18 minutes
Demold Time @ 77°F (25°C)	

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5 - 7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 180°F (82°C). Support of the part may be required to prevent part deformation during heat cure.

VACUUM DE-GASSING/ DE-AIRING:

It is advisable to evacuate entrapped air prior to casting this system. The use of a de-airing agent, (BJB's AF-7) will aid in this process when either de-airing the combined A/B mixture or when de-airing the "A" and "B" components separately.

NOTE:

TC-886 A/B FR with its non-mercury catalyst system does exhibit greater sensitivity to moisture than do similar products that use mercury-containing catalysts. If further information is required, please contact BJB's technical staff for assistance.

STORAGE:

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from the date of shipment when properly stored at room temperature. Purge opened containers with dry nitrogen before re-sealing.

PACKAGING:

Gallon Kits	lbs. A, 6.8 lbs. B
5 Gallon Kits	lbs. A, 34 lbs. B

SAFETY PRECAUTIONS:

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

IF CONTACT OCCURS:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin.

Seek qualified medical attention if allergic reactions occur.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

voliding only as directed by medical personner. The of give anything by moduli to an unconst

Refer to the Material Safety Data Sheet before using this product.

TC-886 A/B FR Page 2 of 2

02/15/2007