

# F-85 A/B 85 SHORE A POLYURETHANE ELASTOMER RATIO: 60/100

#### **PRODUCT DESCRIPTION**:

The F-85 A/B system is a production oriented fast gel and fast de-mold material. It features a working time which allows time to mix, vacuum de-gas, and pour air-free parts. F-85 A/B can be demolded in as little as one hour depending on part size and configuration.

## **PRODUCT HIGHLIGHTS**:

- Rapid demolds
- ➤ Ideal for part production
- > Does not contain MOCA, MDA, or TDI
- Very easy to use

# **PHYSICAL PROPERTIES**:

Hardness, Shore A ASTM D2240	85 + 5
Density, (g/cc) ASTM D792	
Cubic Inches per Pound	
Color/Appearance	
Tensile Strength, (psi) ASTM D412	2,500
Elongation, (%) ASTM D412	275
Tear Strength, (pli) ASTM D624	180
Shrinkage, (in/in) linear ASTM D2566	0.003

### **HANDLING PROPERTIES**:

Mix Ratio (by weight):	
Part A	60 parts by weight
Part B	100 parts by weight
Mix Ratio (by volume):	
Part A	57 parts by volume
Part B	100 parts by volume
Specific Gravity:	
Part A	1.12
Part B	1.06
Viscosity, (cps) @ 77°F (25°C) Brookfield:	
Part A	500
Part B	2,800
Mixed	2,000

#### **HANDLING PROPERTIES (continued):**

#### Color:

Part A	Pale yellow
Part B	Pale amber
Work Time, 100g mass @ 77°F (25°C)	4 minutes
Gel Time	5 minutes
Demold Time @ 77°F (25°C)	1 - 2 hours

#### **CURE SCHEDULE/HEAT CURING:**

Most of the physical properties can be achieved in 5-7 days at ambient temperature,  $77^{\circ}F$  (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature,  $77^{\circ}F$  (25°C), followed by 16 hours at  $160^{\circ}F$  ( $71^{\circ}C$ ).

#### NOTE:

Prolonged direct exposure to sunlight can affect the surface of this product. Cover molds or other products when storing outdoors.

#### STORAGE:

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly store at room temperatures. Purge opened containers with dry nitrogen before re-sealing.

#### **PACKAGING**:

1 Gallon kits	4.8 lbs. A, 8 lbs. B
5 Gallon kits	24 lbs. A, 40 lbs. B
55 Gallon kits	

#### **SAFETY PRECAUTIONS:**

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction.

Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

#### **IF CONTACT OCCURS:**

**Skin:** Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek

qualified medical attention if allergic reactions occur.

**Eyes:** Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce

vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious

person.

Refer to the Material Safety Data Sheet before using this product.

F-85 A/B Page 2 of 2

08/19/2008

For more information call BJB Enterprises, Inc. (714) 734-8450 Fax (714) 734-8929