

# Stereolithography Materials

**SL**  
DIRECT

# Accura<sup>®</sup> SL 5530

for use on  
**SLA 350/3500/5000**  
system

## High Temperature Resistant Stereolithography Material

- High temperature resistance
- Very high throughput material
- Good water resistance
- Suitable for under-the-hood applications
- Suitable for electrical applications
- Resistant to automotive fluids

### Liquid Material

MEASUREMENT	CONDITION	VALUE
Appearance		Clear Amber
Density	@ 25°C (77°F)	1.19 g/cm <sup>3</sup>
Viscosity	@ 28°C (82°F)	270 cps
Viscosity	@ 30°C (86°F)	210 cps
Penetration depth (Dp)		5.4 mils (5.6 mils on SLA 350/3500 systems)
Critical exposure (Ec)		8.9 mJ/cm <sup>2</sup> (9.4 mJ/cm <sup>2</sup> on SLA 350/3500 systems)
Part building layer thickness*		0.05 mm (0.002 in) 0.10 mm (0.004 in)

### Post-Cured Material

\*Dependent upon part geometry and build parameters.

MEASUREMENT	CONDITION	VALUE	VALUE
		90-minute UV post-cure	90-minute UV + 2 hours @ 160° thermal post-cure
Hardness, Shore D	ASTM D 2240	88	90
Flexural modulus	ASTM D 790	2,620 - 3,240 MPa (380 - 470 KSI)	3,496 - 3,634 MPa (507 - 527 KSI)
Flexural strength	ASTM D 790	63 - 87 MPa (9,100 - 12,600 PSI)	96 - 108 MPa (13,900 - 15,700 PSI)
Tensile modulus	ASTM D 638	2,889 - 3,144 MPa (419 - 456 KSI)	3,585 - 3,758 MPa (520 - 545 KSI)
Tensile strength	ASTM D 638	57 - 61 MPa (8,300 - 8,900 PSI)	47 - 61 MPa (6,800 - 8,900 PSI)
Elongation at break	ASTM D 638	3.8 - 4.4%	1.3 - 2.9%
Impact strength, notched Izod	ASTM D 256	21 J/m (0.4 ft - lbs/in)	21 J/m (0.4 ft - lbs/in)
Heat deflection temperature	ASTM D 648 @ 66 PSI @ 264 PSI	70 - 85°C (158 - 185°F) 55 - 58°C (131 - 136°F)	170 - 250°C (338 - 482°F) 110 - 120°C (230 - 248°F)
Glass transition, Tg	DMA, E" peak	79°C (174°F)	122°C (252°F)
Coefficient of thermal expansion	TMA (T<Tg) TMA (T>Tg)	76 x 10 <sup>-6</sup> /°C 152 x 10 <sup>-6</sup> /°C	84 x 10 <sup>-6</sup> /°C 159 x 10 <sup>-6</sup> /°C
Thermal conductivity		0.173 W/m °K 4.2 x 10 <sup>-4</sup> cal/sec.cm.°C	
Density		1.25 g/cm <sup>3</sup>	



**3DSYSTEMS**

3D Systems Corporation  
333 Three D Systems Circle  
Rock Hill, SC 29730, USA

Tel.: +1 803.326.3900  
NYSE: DDD  
www.3dsystems.com

### MANUFACTURING THE FUTURE

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use. © 2015 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo and Accura are registered trademarks of 3D Systems, Inc.